WHAT IS CLAIMED IS:

1. A polyamide composition for welding comprising

(A) an aromatic polyamide having a molar fraction of aromatic monomers among monomer components of said polyamide of at least 0.2, and

(B) an aliphatic polyamide,

wherein the weight ratio of (A) and (B) is from 99:1 to 20:80.

2. A polyamide composition for welding comprising

(A) an aromatic polyamide having a carboxylic acid component consisting of terephthalic acid, isophthalic acid or a mixture of terephthalic acid and isophthalic acid and optionally aliphatic acid; and a diamine component of aliphatic diamine, and,

(B) aliphatic polyamide,

wherein the weight ratio of (A) and (B) is from 99:1 to 5:95.

3. A polyamide molded article comprised of two or more members, wherein at least two of the members have been welded using the polyamide composition for welding of Claim 1.

4. The composition of claim 2 wherein said aromatic polyamide comprising the carboxylic acid component being terephthalic acid or a mixture of terephthalic acid and isophthalic acid; and the diamine component being hexamethylenediamine or a mixture of hexamethylenediamine and 2-methyl pentamethylenediamine.

5. A polyamide composition for welding comprising

(A) an aromatic polyamide wherein the carboxylic acid component is aliphatic dicarboxylic acid; and the diamine component is aromatic diamine or a mixture of aromatic and aliphatic diamines, and

(B) aliphatic polyamide,

wherein the weight ratio of (A) and (B) is from 50:50 to 95:5.